

Technical data sheet in accordance with ASTM

Material

NBR NB903411

black

cross linking: sulfur

revision index

2

revision date

2/5/2024

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D297	1.32 ±0.02	1.32	g/cm ³
Hardness ASTM D2240, Shore A	90 ±5	88	Shore
Tensile strength ASTM D412	---	16.6	MPa
Elongation at break ASTM D412	---	119	%
Compression set ASTM D395, 22 h, 100 °C	---	6	%
Temperature range	-35°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free Info ROHS and ELV			see certificate EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC see DoC

Change after aging in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	88	91	3
Tensile strength (ASTM D412)	MPa	16.6	15.9	-4 %
Elongation at break (ASTM D412)	%	119	101.1	-15 %

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

Material

NBR NB903411

black

cross linking: sulfur

revision index

2

revision date

2/5/2024

page 2 / 3

Change after aging in Fuel A: 70h/23°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

	Base value	After aging	difference
Shore	88	88	0
MPa	16.6	14.3	-14 %
%	119	113	-5 %
%		0	

Typ. values

Change after aging in Fuel B: 70h/23°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

	Base value	After aging	difference
Shore	88	79	-9
MPa	16.6	12.4	-25 %
%	119	94	-21 %
%		12	

Typ. values

Change after aging in IRM 901: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

	Base value	After aging	difference
Shore	88	93	5
MPa	16.6	15.4	-7 %
%	119	96.4	-19 %
%		-5	

Typ. values

Change after aging in IRM 903: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

	Base value	After aging	difference
Shore	88	86	-2
MPa	16.6	16.4	-1 %
%	119	104.7	-12 %
%		5	

Typ. values

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

Material

NBR NB903411

black

cross linking: sulfur

revision index

2

revision date

2/5/2024

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -

Fax: -

Email: FIS.Compound.CRC@fst.com

